



RC PLAST

Plastic recycling with
care and competence

Data Sheet: 541-287 PP-C 40-50 Sort

This PP is recycled from first class industrial non-woven. The non-woven itself is processed from raw material which is 82 % virgin high quality PP Homopolymer and 18 % PE.

Property	Value		Unit	Standard
	Min	Max		
Physical Properties				
Melt flow rate (2,16kg,230°C)	35	55	g/10min	ISO 1133
Density	0,94	0,96	g/cm ³	ISO 1183
Mechanical Properties				
Tensile strength at yield			MPa	ISO 527
E-Modul			MPa	ISO 527
Charpy (notched)	1,8	2,1	kJ/m ²	ISO 179
Thermal Properties				
Vicat softening point (10N,100°C/h)	140	145	°C	ISO 306

Applications

Injection moulding

Packaging

Big bag, approx. 1100kg

Bulk, approx.: 25t

These data are not exact values. They represent an average of the values obtained during laboratory analysis.

Rc Plast A/S
Gellerupvej 112
6800 Varde, Danmark